ডিপি-৫

# RESTRICTED

ক্রোড়পত্র ঘ ডিজিডিপি দরপত্র নং ২১৯.২১৬.২৩ তারিখ ০৮ এপ্রিল ২০২৪

# **TECHNICAL SPECIFICATION**

OF

# ITEM NO 1,H-1 (C)/HA-6048,MINERAL HYDRAULIC OIL (ISO VISCOSITY GRADE - 15)

Ser	Characteristics	Unit	Specified Limit	Rmks
1.	Specific gravity at 15°C	Kg/Litre 0.855 ~ 0.870		
2.	Kinematics Viscosity at 40°C	cSt	13.5 ~ 16.5	
3.	Kinematics Viscosity at 50°C	cSt	10.7~11.8	*************************
4.	Viscosity Index (Min)	No	60	
5.	Flash Point (COC) (Min)	ಿ೦	163	
6.	Neutralization Value (Max)	mg KOH/gm	0.20	***************************************
7.	Pour Point (Max)	°C	-42 (Max)	***************************************







#### RESTRICTED

ANX 'B' TO IA&E LTR NO.23.01,903,052.12.135.01,2024. 24.03.2024 DT 2A MAR 2024

#### **TECHNICAL SPECIFICATION**

OF

# ITEM NO 3, H-1 (C)/HA-6047, HYDRAULIC FLUID (GLYCERINE BASED)/ RECUPERATOR OIL, RECOIL LIQUID NO 1 (WITH ETHANOL)

- 1. <u>Description</u>: Hydraulic Fluid is a transparent Glycerine based solution. Initially it is prepared as two separate solution to increase it's shelf life only and the solutions are known as solution no. 1 and solution no. 2. On mixing them in the 4.81:1 ratio the final solution of the Recuperator oil, Recoil Liquid no -1 (with Ethanol) is obtained. Innascent stage it is yellowgreen in colour and become dark green in the passage of time.
- 2. <u>Composition</u>. Hydraulic Fluid (glycerin based) or Recuperator Oil, Recoil Liquid no 1 (with Ethanol) is composed of following ingredients:

a.	Pure Glycerine :				47 % (by weight)
	Purity	-	99 %		
	Sp gr	-	1.256 ~ 1.261		
b.	Ethanol:			į	19 % (by weight)
	Purity		95.5 % alcohal		, , , , ,
	Water	-	4.5 % (max)		
C.	Distilled water:			3	31.6 % (by weight
	P <sup>H</sup> Value		5.5 ~ 7.5		
	Hardness		Nil		
d.	Potasium chromate solid :			*	2.3 % (by weight)
	Purity		99 % (min)		
	PHValue (5% aqueous solution)		8.5 ~ 10		
e.	Sodium Hydroxide:			:	0.1 % (by weight)
	Purity	-	97 %(min)		
	Carbonate	-	2 %(max)		

- 3. <u>Method of preparation</u>. (For 1 litre of Hydraulic Fluid Glycerine based)
  - a. Solution no. 1
    - (1) 402 ml of Glycerine and 266 ml of Ethanol are mixed in a container.
    - (2) 1.06 gm sodium Hydroxide is mixed with 160 ml of distilled water.
    - (3) Add mixture as in para 3a (2) to mixture in para 3a (1) to make solution no.1
  - b. Solution no. 2
    - 23 gm of Potassium chromate is dissolved in 167 ml distilled water which is known as solution no.2.
  - c. To make the Recuperator oil, Recoil Liquid no.1 (with Ethanol) solution no.2 is added slowly with continuous stirring to solution no.1 in ratio 1:4.81 (by volume). The solution no.1 and solution no.2 should be mixed before use.
- 4. <u>Packing</u>: For each 17.5 litre mixture of Recuperator oil, Recoil Liquid no.1 (with Ethanol), 3.01 litres solution no.2 and 14.49 litres solution no.1 should be packed in two separate glass (Amber colour)/ plastic (white colour) containers of capacity 3.5 litres and 20 litres respectively.

SERVERAL DEFENCES

#### RESTRICTED

5. Marking: Following marking/instructions should be pasted/printed on each container:

प्रवन नः .....

### HA-6047, HYDRAULIC FLUID (GLYCERINE BASED) এর ব্যবহার বিধি

দ্রবন নং ২ (৩.০১ লিটার), দ্রবন নং ১ (১৪.৪৯ লিটার) এর মধ্যে ঢেলে উত্তম রূপে মিগ্রিত করে নিলেই ১৭.৫ লিটার "HA-6047, Hydraulic Fluid (Glycerin Bassed)" ব্যবহারের জন্য প্রস্তুত হবে।

বিশেষ দ্রষ্টব্য ঃ দ্রবন নং ১ ও দ্রবন নং ২, এর মিশ্রণ তারিখ থেকে মিশ্রিত "HA-6047, Hydraulic Fluid (Glycerin Based)" এর আয়ুদ্ধাল গণনা করতে হবে।

প্রধান পরিদর্শক আই এ এভ ই

#### অন্যান্য শর্তাবলী ঃ

- ক। বিনির্দেশের ভিত্তিতে সমৃদয় পণ্য সরবরাহ করিতে হবে।
- খ। পণ্যের ধারক সমূহ সম্পূর্ণ বায়ু নিরোধী হবে।
- গ। পরিদর্শন নির্দেশাবলী ঃ
  - (১) পুর্ণ সরবরাহের পূর্বে অগ্রিম নমুনা (ধারকসহ পণ্যের উপকরণ সমূহ) অবশ্যই পরিদর্শনালয় কর্তৃক অনুমোদিত হতে হবে। টেভার /অগ্রিম নমুনা অত্র পরিদর্শনালয় কর্তৃক অনুমোদন করাইতে হবে। উল্লেখ্য যে, টেভার/অগ্রিম নমুনা পেশ করার কালে পণ্যটির উপকরণ সমূহ পৃথক পৃথক ভাবে উপস্থাপন করতে হবে।
  - (২) সরবরাহকারীর প্রান্তে সমৃদয় উপকরণ (Bulk store) এবং ধারক সমূহ পরিদর্শনালয় কর্তৃক পরিদর্শন করাইয়া লইতে হবে।
  - পরিদর্শনালয়ের প্রতিনিধির উপস্থিতিতে উপকরণ সমুহের সংমিশ্রণ করতে হবে।
- ঘ। প্রতিটি ধারকের গায়ে "সেনাবাহিনী" কথাটি অমোচনীয় কালি দ্বারা সীল মোহর করে দিতে হবে।



B-2/2 RESTRICTED

